

## Interpon D1010 Textura®: Durability Test Report



The new Interpon Textura® is the ideal finish for powder coating surfaces where marring and wrap marking need to be reduced.

Our in-house laboratory analysis has proven Textura's durability and resilience across a number of tests against standard coatings.

### Global Trends on Textured Finishes

The Akzo Nobel global sales growth in textured powdercoating finishes over the past 3 years has tripled. Globally, textures are proving to be popular with both architects and fabricators alike. Damage resistance and the forgiving nature of the surface are key features for the fabricators while the feel and the appearance of the texture make the surface more organic for architectural design. Textured surfaces' popularity is gaining momentum across the globe.

Interpon D1010 Textura® Black outperformed a standard black matt / satin across two comparative durability tests – Abrasion Resistance Test (Weighted Panel to Panel Rub Test) [T980.7] and Heated Wrap Marking Test.

Interpon Textura® Black	Standard black matt / satin
<b>Test 1: Abrasion Resistance Test (Weighted Panel to Panel) [T980.7]</b>	
Tested for: <ul style="list-style-type: none"> <li>Abrasion</li> </ul>	
<b>Summary</b> Textura® Black performed <b>652</b> times better than standard black matt and satin products.	
<b>Test 2: Heated Wrap Marking Test</b>	
After 1 hour up to 120°C: <ul style="list-style-type: none"> <li>No visible markings</li> </ul>	After 1 hour at 70°C: <ul style="list-style-type: none"> <li>Visible markings and tiger striping</li> </ul>
<b>Summary</b> Testing of Textura® Black stopped at 120°C due to bubble wrap melting / fusing. At this point, Textura® Black did not exhibit any markings.	Markings and tiger striping visible at 70°C.





Textura® White GA331A

Textura® Titania GA375A

Textura® Silver GY34LA

Textura® Sandstone Grey GL381A

Textura® Grey Friars GL365A

Textura® Charcoal GL390A

Textura® Gravel GN368A

Textura® Ironsand GM333A

Textura® Monument GL330A

Textura® Flaxpod GL395A

Textura® Black GN306A

For more information please refer to the Interpon Textura Technical Data Sheet or contact our Customer Service Team on 0800 150 527 or [salesnz@interpon.co.nz](mailto:salesnz@interpon.co.nz).



## Free Interpon Textura Swatch Set

Feel the Interpon Textura difference for yourself!

Contact your Interpon Sales Representative for a free sample swatch set.

# Interpon®

#### DISCLAIMER

AkzoNobel endeavours to ensure the information contained in this publication is correct at the time of printing. All products referred to and any technical advice provided is subject to the standard terms and conditions of sale of the AkzoNobel supplying company. Unless otherwise agreed by us in writing, any contract to purchase products referred to in this color card and any advice that we give in connection with the supply of products are subject to our standard conditions of sale. Typical end uses for Interpon products are displayed in this publication using actual projects and representative images. AkzoNobel would like to acknowledge and thank Altus, Nulokk solutions, Bradnams and Bates Aluminium for the use of their images contained within this brochure. Textura® is a registered trademark of Akzo Nobel Pty Limited. Interpon® is a registered trademark of Akzo Nobel International BV.  
© Copyright 2020 Akzo Nobel Pty Limited ABN 59 000 119 424.

September 2020